

IDEAL (VS) LTD SUITE-151, 100 RYDERS LANE, PEOPLES PLAZA, MILLTOWN NEW JERSEY - 08850, U.S.A

TEL: 732-246-0337 FAX: 732-246-0523

	GREY TAP	PE SPECII	FICATI	ONS
PRODUCT DESCRIPTION	GREY TAPE IS A SELF WOUND POLYETHYLENE/SCRIM FACESTOCK COATED ON ONE SIDE WITH AN AGGRESSIVE RUBBER BASED ADHESIVE.			
TEST THICKNESS CARRIER ADHESIVE	TYPICAL VALUES (NOT U.S. MILS 6.0 1.2	FOR SPECIFICATION METRIC MILLIMETE 0.15 0.03	<u>RS</u>	TEST METHOD PSTC-33 ASTM-D-1000 TAPPI-T-411-M-44
TOTAL	7.2	0.18		17W 1 1 1 7 1 1 W1 7 7
TENSILE ELONGATION	U.S. POUNDS FORCE PER INCH WIDTH 27 10%	METRIC NEWTONS PER METER 4725 10%		ASTM-D-882-61T ASTM-D-882-61T
ADHESION, 180° PEEL	2 MIL (0.05 MM) POLYE U.S. OZ. FORCE PER INCH WIDTH	STER SUPPORT METRIC NEWTONS PER METER		
SUBSTRATE: STAINLESS STEEL (APPLIED ONE MINUTE)	40	435		PSTC-3 ASTM-D-3330
TACK, LOOP	U.S. OZ. FORCE PER INCH 48	METRIC NEWTONS PER METER 525		TM-7A
SHEAR, STATIC	AREA 1 IN ² (6.6 CM ²) 0.25 IN ² (1.6 CM ²)	LOAD 5.5 LB (2.6 KG) 2.2 LB (1 KG)	AVERAGE V (MINUTES) > 50 > 10	PSTC 7, FEDERAL TEST, METHOD 147B
APPLICATIONS	GREY TAPE IS DESIGNED FOR APPLICATIONS REQUIRING AN AGGRESSIVE ADHESIVE FOR THE SEALING OF JOINTS AND SEAMS IN THE INDUSTRIAL INSULATION MARKET.			
SURFACE PREPARATION	IT IS ESSENTIAL, AS WITH ALL PRESSURE SENSITIVE TAPES, THAT THE SURFACE TO WHICH THE TAPE IS APPLIED BE CLEAN, DRY AND FREE OF GREASE AND OIL SQUEEGEE TAPE FLAT.			
STORAGE & SHELF LIFE	ONE YEAR WHEN STORED AT 70°F (21°C)/50% RELATIVE HUMIDITY OUT OF DIRECT SUNLIGHT.			
FEATURES AND BENEFITS	FEATURES * RUBBER BASED ADHESIVE * AGGRESSIVE TACK & ADHESION FOR AIR TIGHT MOISTURE RESISTANT SEAL. * SCRIM REINFORCED FACE STOCK * STRAIGHT TEARING DURING APPLICATION WITH NO CURL.			
COMPOSITION	FACESTOCK: 6.0 MILS (0.15 MM) POLYETHYLENE COATED SCRIM. ADHESIVE: 1.2 MILS (0.03 MM) AGGRESSIVE RUBBER BASED ADHESIVE. Rev.			